




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B32B 31/30, 15/08, B29C 47/02	A1	(11) International Publication Number: WO 98/52750 (43) International Publication Date: 26 November 1998 (26.11.98)
(21) International Application Number: PCT/EP98/03001 (22) International Filing Date: 14 May 1998 (14.05.98) (30) Priority Data: 1006109 22 May 1997 (22.05.97) NL (71) Applicant (for all designated States except US): HOOGOVENS STAAL B.V. [NL/NL]; P.O. Box 10000, NL-1970 CA IJmuiden (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): BEENTJES, Petrus, Cor- nelis, Jozef [NL/NL]; Cieweg 43, NL-1902 AA Castricum (NL). VAN VEENEN, Willem, Jan [NL/NL]; Plesmanweg 67, NL-1945 WL Beverwijk (NL). (74) Agent: HERMAN DE GROOT, Johan, Willem; Hoogovens Corporate Services B.V., P.O. Box 10000, NL-1970 CA IJmuiden (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: METHOD OF COATING A METALLIC SUBSTRATE WITH THERMOPLASTIC COATING MATERIAL		
(57) Abstract		
<p>Method of coating a metallic substrate (1) with thermoplastic coating material, comprising a preheating the substrate in such a way that, just prior to coating, it is at a temperature between 70 °C and 150 °C, preferably between 100 °C and 130 °C in the case of a coating containing polypropene and between 80 and 110 °C in the case of a coating containing polyethylene; coextrusion, in the first coating station of a sheet (6) comprising a polyolefin covering layer and a modified polyolefin adhesion layer; coating of the substrate (1) with a molten sheet in the presence of ozone by pressing it with the adhesion layer against the surface of the substrate; transportation of the strip (9) coated on one side to a second coating station and heating the strip so that, just before coating, the strip is at a temperature between 70 °C and 130 °C, preferably between 80 °C and 120 °C, if the coating layer applied in the first coating station is polypropene and between 80 and 110 °C if the coating layer applied at that point is polyethylene; coating of the substrate with a molten sheet extruded in the second coating station by pressing it against the uncoated surface of the substrate, use being made of the presence of ozone; heating of the coated substrate so that it assumes a temperature which is above the melting point of the polyolefins applied; cooling of the coated substrate.</p>		



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD OF COATING A METALLIC SUBSTRATE WITH
THERMOPLASTIC COATING MATERIAL

The invention relates to a method of coating a metallic substrate with thermoplastic coating material.

5 In connection with this application, thermoplastic materials must also be understood to mean plastic materials which are composed essentially of thermoplastics and furthermore of additives which are added to obtain particular properties.

10 The coating of metallic substrates with plastic layers is known in practice and is suitable, in particular, where the metal used has to be protected against atmospheric, generally corrosive, conditions or where the environment has to remain safeguarded from
15 undesirable action of the metal or where both the abovementioned effects have to be avoided, such as in the case of packagings. Certain foodstuff cans, for example, have long been manufactured from tinned packaging steel, also called tinplate, provided on one side with a plastic
20 layer in order to prevent the metal from entering the foodstuff and from rusting through occurring as a consequence of corrosive action of the foodstuff and, on the other hand, to preserve the fine appearance of the packaging for a sufficiently long time.

25 These coating layers, which are usually organic, are generally applied by lacquering. It may be necessary to apply different covering layers for the inside and outside of the lid. The covering layer on the inside must primarily offer a good corrosion protection against the
30 respective product to be preserved and to be packaged, while, on the outside, the appearance, for example, the gloss and the colour, and mechanical resistance to scratching and impacts are of importance.

A machining step in the creation formation of a
35 packaging, such as the folding of body and lid in the case of a foodstuff can or drink can, may give rise, for example, to the imposition of more detailed requirements on the covering layer. It is of importance that the covering layer on the outside is both scratch-resistant

and readily deformable so that the folding operation is withstood without damage.

To apply an organic top coat, apart from lacquering of the partly finished packaging, it is also conceivable to carry out the coating at an earlier stage in the production chain in the form of a coil-coating process, for example coil lacquering, foil film coating (also referred to as coil laminating), in which a plastic film is applied to a substrate, and extrusion coating, a form of film coating in which the film is not supplied from elsewhere, but, as it were, is produced by extrusion at the point which is being coated and applied to a substrate.

Any method of coating has its own disadvantages, be it in the nature of the coating material or in the nature of the manner of coating. It is clear that the drawback of evaporation of solvents applies to lacquering, which is even a very great drawback if the solvents contain VOCs (= volatile organic compounds), which is the case for many applications.

Film coating is generally not regarded as an economically feasible alternative. The production of the film, rolling it up, transporting it and unrolling it again result, when taken together, in an alternative which does not compete with lacquering.

The extrusion coating process as a method of application is attractive because it does not have the abovementioned economic disadvantage, but it proves difficult to carry out in the case of certain combinations. This applies mainly to single-sided or double-sided coating with polyolefins. Said polyolefins do not inherently have the properties which are necessary for good adhesion to metal substrates. For this reason polyolefin coating layers are usually chosen which are provided with a modified adhesion layer. Said adhesion layer is then composed of polyolefins modified with carboxylic acid groups or anhydride groups. Suitable adhesion layers based on polyolefins can be produced, for example, by copolymerization of propene or ethene or a

combination of the last two with α -unsaturated carboxylic acids, β -unsaturated carboxylic acids, the associated anhydrides or associated esters or half-esters. Examples of these are acrylic acid, methacrylic acid, crotonic acid, cinnamic acid, maleic acid, maleic anhydride, fumaric acid and the like. The percentage by weight of such modifying monomers is normally between 1 and 15%.

Such adhesion-promoting monomers are capable of binding to the substrate surface but do so only if the polyolefin adhesion layer is at a temperature above the melting point for some time, as a result of which diffusion of the adhesion-promoting monomers through the polyolefin to the substrate surface becomes possible and the adhesion-promoting monomer may react chemically or physically with the substrate surface. It is found to be impossible to bring about adequate adhesion for further transportation of the product through the line by means of extrusion of a polyolefin provided with adhesion-promoting monomers onto a metal substrate which is brought to a temperature which is below the melting point of the respective polyolefin. Instead of that, the film follows the track of the internally cooled metal pressure roller which presses the coating layer onto the substrate and the film is rolled up onto the pressure roller. Preheating the metal strip to a temperature above the melting point of the polyolefin is, of course, very readily possible. This results in an adhesion between the modified polyolefin coating layer and the metal strip. However, if the other side of the strip has also to be coated and this does not take place at the same time as the coating of the abovementioned side, the problem arises that the coating layer of the abovementioned side is damaged during the step of coating the other side because the temperature of the product is, after all, above the melting point of the polyolefin coating layer. As a result, the coating layer comes into contact with the steel pressure roller in the molten and, consequently, very fragile state and is damaged.

In regard to the modification of the plastic

film, such as, for example, by means of oxidation of the surface by a corona treatment, extrusion at very high temperature or a flame treatment, it may be pointed out that these are generally not readily feasible for the in situ modification of a molten, very thin sheet of plastic. A corona treatment ensures the production of an electrostatic charge, as a result of which the molten sheet is repelled from the corona installation and the treatment loses its effectiveness. In the case of extrusion of the polyolefin at very high temperature, the free surface of the coating layer oxidizes, resulting in the packaging material having an increased effect on the taste of the filling agent; a flame treatment is accompanied by a gas flow which repels the molten sheet of plastic and, in addition, develops a fairly large amount of heat around the mouth of the gun head.

Surprisingly, modification can in fact be carried out successfully by making use of a very small amount of ozone gas, which oxidizes the surface of the sheet of molten polyolefin in such a way that some adhesion to a substrate which is at a preheating temperature lower than the melting point of the polyolefin is produced even in the laminating nip. This in-situ adhesion is found to be adequate for the coating layer to follow the substrate and, consequently, not the internally cooled pressure roller, to the afterheating section, where further adhesion improvement takes place by afterheating to a temperature above the melting point of the polyolefin, followed by diffusion of the adhesion-promoting groups to the substrate surface and further chemical or physical reactions.

It is furthermore found that copolymerization of propene with ethene has the result that the action of the ozone gas is improved, as a result of which the initial adhesion of the coating layer to the substrate increases.

The method according to the invention now comprises:

- preheating of the substrate in such a way that, just prior to coating, it is at a temperature

- between 70°C and 150°C, preferably between 100°C and 130°C in the case of a coating containing polypropene and between 80 and 110°C in the case of a single-sided or double-sided coating containing polyethene;
- 5 -
- coextrusion, in a first coating station of a sheet comprising a polyolefin covering layer and a modified polyolefin adhesion layer;
-
- 10 coating of the substrate with a molten sheet in the presence of ozone by pressing it with the adhesion layer against the surface of the substrate;
-
- 15 transportation of the strip coated on one side to a second coating station and heating the strip so that, just before coating, the strip is at a temperature between 70°C and 130°C, preferably between 80°C and 120°C, if the coating layer applied in the first coating station is polypropene, and between 80 and 110°C, if the coating layer applied at that point is polyethene;
- 20 -
- coating of the substrate with a molten sheet extruded in the second coating station by pressing it against the uncoated surface of the substrate, use being made of the presence of ozone;
- 25 -
- heating of the coated substrate so that it assumes a temperature which is above the melting point of the polyolefin applied;
- 30 -
- cooling of the coated substrate.

An alternative method according to the invention comprises:

-
- 35 preheating the substrate in such a way that, just prior to coating in a first coating station, it is at a temperature between 70°C and 150°C, preferably between 100°C and 130°C;
-
- extrusion, in the first coating station, of a molten sheet of polyester composed of one or more layers of polyester;

- coating of the substrate by pressing the molten sheet against a surface of the substrate;
- transportation of the strip coated on one side with polyester to a second coating station and heating the strip so that, before coating, it is at a temperature between 70°C and 130°C, preferably between 90°C and 120°C;
- coextrusion, in a second coating station, of a sheet comprising a polyolefin top layer and a modified polyolefin adhesion layer;
- coating of the substrate with the molten sheet in the presence of ozone by pressing it with the adhesion layer against the surface of the substrate;
- heating the coated substrate so that it assumes a temperature which is above the melting point of the polyolefin applied;
- cooling of the coated substrate.

As a result of a suitable cooling treatment, for example preferably by quenching in water, the thermoplastic coating layer remains as amorphous as possible in the case of a polyester as coating layer, or particularly monocrystalline in the case of a polyolefin as coating layer. A coated substrate produced in this way is capable of withstanding deformations, for example as a consequence of folding treatment, well. Recrystallization does in fact occur again to a certain degree as a result of heating at a later point in time, for example in connection with sterilization; however, this does not then constitute a disadvantage but, on the contrary, an advantage. As a result of recrystallization, the crystallinity and, consequently, the hardness of the covering layer increases.

It may be beneficial to add LDPE to the thermoplastic material at preferably 5-20% by weight. This results in a better workability of the molten sheet, with improved initial adherence after ozone treatment.

According to the invention, a metallic substrate coated with a thermoplastic material is obtained, in

which the thickness of the substrate is 0.05-0.30 mm and the thickness of the thermoplastic coating layer is 3-50 μm .

5 The plastic layer is applied, for example, with an extruder, with which a multilayer system may also be applied.

10 Polyolefins such as PP and PE are applied in molten form to a metal substrate, for example as shown in Figure 1. The distance of the lips of the nozzle from the nip between two rollers is between 4 and 25 cm, preferably between 8 and 20 cm. Such a method of application is possible for plastics having a fairly low melt strength, such as polyesters, only at a low stretch ratio, that is to say low strip speed.

15 The ozone is concentrated between the molten sheet and the substrate. The outlet opening of the application system is directed towards the molten sheet. As a result of the extremely small amount of gas which is necessary, the web of the molten sheet is not disturbed.

20 As a result of the method of application and in conjunction with the heat treatment, it is preferable, wherever possible, for the thickness of substrate and coating layer to be within the specified ranges.

25 Preferably, the thickness of the thermoplastic coating layer varies in the range from 3 to 20 μm . The molten sheet is already thin and, as a result of the correct feed rate in combination with a suitable substrate speed, can still be thinned down into the specified range as a consequence of uniaxial stretching.

30 From the point of view of material consumption, as thin a plastic layer as possible is desirable. From a functional point of view, however, a higher lower limit than 3 μm may apply, depending on the application. The metallic substrate may be essentially iron-containing,

35 for example steel. This is a cheap and attractive material with a view to reusability (possibility of recycling). Furthermore, an essentially iron-containing substrate can readily be heated by means of induction and the temperatures used in the present method do not have

any appreciable effect on the mechanical properties of the substrate. For good adhesion, a packaging steel of the ECCS type is suitable.

5 A packaging steel coated with a thermoplastic material containing essentially PP is, for example, particularly suitable for so-called lid applications. From test results on cans stored in conditioned rooms, manufactured with material according to the invention and filled with foodstuffs, it is found that very good
10 results are achieved with lid material of packaging steel according to the invention provided with a PP coating layer. The material produced in this way is found both to have good corrosion resistance and to be scratch-resistant, so that the same layer can be used both inside
15 and outside the foodstuffs can, i.e. in a double-sided manner on the starting material. Coated material can also be processed without difficulty in the manner disclosed.

Exemplary Embodiment 1

20 The application of a PP covering layer to both sides of the strip proceeds, for example, as follows:

- an already chromium-plated steel substrate (ECCS = electrolytically chrome-coated steel) is preheated to 130°C;
- the heated substrate is passed through a coating
25 nip formed by a rubber pressure roller and a polished, cooled roller;
- in said nip, a sheet of molten PP having a width which is 10 to 40 mm greater than the width of the substrate and composed of the adhesion layer,
30 which comes into contact with the substrate, and the top layer, the top layer being thicker than the adhesion layer, is applied to the substrate from a system comprising two extruders, the plastic flows emerging from which are combined in
35 a coextrusion die head;
- an amount of ozone gas is directed at the molten sheet and, specifically, as low as possible, just in front of the nip so that the percentage of

- fresh surface is a maximum at that point. An amount of 8 mg/ozone per m² is adequate;
- the laminate of ECCS and PP formed is cooled only over the contact length of the nip by the polished cooling roller so that the PP layer applied assumes the roughness of the cooling roller but the temperature of the laminate falls by only a small amount;
- 5
- the oxidation of the polyolefin surface in contact with the steel substrate ensures that the coating layer adheres sufficiently to the steel substrate for it to be able to peel off the internally cooled pressure roller;
- 10
- the substrate, which is now coated on one side, is brought in the same line section to a temperature of 120°C and is also provided on the other side with a polyolefin plastic layer in the presence of ozone gas;
- 15
- still in the same line section, the strip coated on two sides is then heated by means of induction heating between 150°C and 280°C, preferably between 180°C and 225°C, kept at this temperature for 0.5 to 20 seconds and then very rapidly cooled in a water tank;
- 20
- this is followed by drying using wringer rollers or hot air;
- 25
- after the plastic layers have been applied to both sides of the strip and the adhesion has been maximized, the excess of plastic is removed at both edges of the strip by means of a suitable cutting technique, such as laser cutting or water cutting;
- 30
- finally, the coated strip is rolled up or cut into plates;
- 35
- from the packaging steel coated in the abovementioned manner, lids, for example, are produced in the usual way. These lids are then provided with a suitable compound in the usual manner. The compound applied is then dried in a

convection oven under conditions such that the lids reach a temperature of 110 to 150°C, preferably of 110 to 120°C. The lids produced in this way are found to perform better than lids produced from ECCS having the same thickness and the same quality and provided on both sides with a 5-g/m² lacquer layer.

Exemplary Embodiment 2

As Exemplary Embodiment 1, but in this case a polypropene coating layer composed of a combination of a homopolymeric adhesion layer and a homopolymeric top layer and then a polyester coating layer is first applied:

- an already chromium-plated steel substrate (ECCS = electrolytically chrome-coated steel) is preheated to 130°C;
- the heated substrate is passed through a coating nip formed by a rubber pressure roller and a polished, cooled roller;
- in said nip, a sheet of molten PP having a width which is 10 to 40 mm greater than the width of the substrate and composed of the adhesion layer, which comes into contact with the substrate, and the top layer, the top layer being thicker than the adhesion layer, is applied to the substrate from a system comprising two extruders, the plastic flows emerging from which are combined in a coextrusion die head;
- an amount of 8 mg/ozone per m² of ozone gas is directed at the molten sheet and, specifically, as low as possible, just in front of the nip so that the percentage of fresh surface is a maximum at that point;
- the laminate of ECCS and PP formed is cooled only over the contact length of the nip by the polished cooling roller so that the PP layer applied assumes the roughness of the cooling roller but the temperature of the laminate falls

- by only a small amount;
- the oxidation of the polyolefin surface in contact with the steel substrate ensures that the coating layer adheres just enough to the steel substrate to be able to peel off the internally cooled pressure roller;
 - the substrate, which is now coated on one side, is brought in the same line section to a temperature of 120°C and is also provided on the other side with a polyester coating layer;
 - still in the same line section, the strip coated on two sides is then heated by means of induction heating between 150°C and 280°C, preferably between 210°C and 265°C, kept at this temperature for 0.5 to 20 seconds and then very rapidly cooled in a water tank;
 - this is followed by drying using wringer rollers or hot air;
 - after the plastic layers have been applied to both sides of the strip and the adhesion has been maximized, the excess of plastic is removed at both edges of the strip by means of a suitable cutting technique, such as laser cutting or water cutting;
 - finally, the coated strip is rolled up or cut into plates.

Exemplary Embodiment 3

Instead of a homopolymeric adhesion layer, a copolymeric adhesion layer is now chosen which also contains a percentage of PE. Under exactly the same conditions, the adhesion is found to be very reliable and completely suitable for further processing immediately after the nip 1.

Comparison Example 1

As Example 1, but without ozone.

After applying the molten sheet in the nip, internally cooled steel pressure rollers are found to

pull the polyolefin coating layer produced off the strip, regardless of the roughness of said rollers, as a result of which air comes between the substrate and the coating layer, even if the starting section of the coating layer is securely stuck to the substrate with tape. As a result of this penetration of air, a very uneven product which cannot be processed is produced in the afterheating oven.

Comparison Example 2

As Example 1, but the preheating temperature of the strip is now 200°C and the ozone generator is switched off.

Depending on the thickness of the molten sheet, it adheres more or less well to the substrate after nip 1. A thickness of the molten sheet below 10 micrometres freezes very rapidly on the internally cooled pressure roller, as a result of which the diffusion of the adhesion-promoting groups quite quickly stops and the adhesion becomes moderate. Thicker coating layers do satisfactorily adhere. In the second nip, however, the temperature of the single-sided coated strip is still 150°C and the polyolefin coating layer already applied in nip 1 is damaged. As a result, a very uneven product is produced.

The invention will now be explained in greater detail by reference to the drawing, in which:

Figure 1 shows a device for carrying out the method according to the invention.

In Figure 1, 1 is a metallic, strip-type substrate which is passed through, for example, an induction oven 2.

The substrate 1, which leaves the oven 2, for example, vertically, is passed round a deflection roller 3 to a first coating station which comprises an extrusion device 4, an ozone generator 5, a pressure roller 8, for example of steel, and a supporting roller 7, preferably provided with a rubber layer. The mouth of the ozone generator 5 is preferably situated as near as possible to the region where the substrate 1 and a sheet 6 emerging

from the extrusion device 4 come together, just in front of the nip between supporting roller 7 and pressure roller 8.

5 After passing the first coating station, a single-sided coated substrate 9 is produced which is passed, possibly via an oven 13, to a second coating station. This station comprises a second extrusion device 10, a second ozone generator 5 and a supporting roller and pressure roller 7 and 8, respectively.

10 After the second coating, the double-sided coated substrate leaves the device via an oven 12.

Extrusion device 4 is suitable for extruding a sheet 6 of polyolefin, for example PP or PE, provided with an adhesion layer or of polyester. The extrusion
15 device 4 possibly comprises an extrusion device for polyolefins and one for polyester and the one chosen is employed. Extrusion device 10 is suitable for polyolefins. It is possible to interchange the positions of extrusion devices 4 and 10.

CLAIMS

1. Method of coating a metallic substrate with thermoplastic coating material, comprising
- 5 - preheating of the substrate in such a way that, just prior to coating, it is at a temperature between 70°C and 150°C, preferably between 100°C and 130°C in the case of a coating containing polypropene and between 80 and 110°C in the case of a coating containing polyethene;
 - 10 - coextrusion, in a first coating station of a sheet comprising a polyolefin covering layer and a modified polyolefin adhesion layer;
 - coating of the substrate with a molten sheet in the presence of ozone by pressing it with the adhesion layer against the surface of the substrate;
 - 15 - transportation of the strip coated on one side to a second coating station and heating the strip so that, just before coating, the strip is at a temperature between 70°C and 130°C, preferably between 80°C and 120°C, if the coating layer applied in the first coating station is polypropene, and between 80 and 110°C if the coating layer applied at that point is polyethene;
 - 20 - coating of the substrate with a molten sheet extruded in the second coating station by pressing it against the uncoated surface of the substrate, use being made of the presence of ozone;
 - 25 - heating of the coated substrate so that it assumes a temperature which is above the melting point of the polyolefin applied;
 - cooling of the coated substrate.
 - 30
 - 35 2. Method of coating a metallic substrate with thermoplastic coating material, comprising:
 - preheating the substrate in such a way that, just prior to coating in a first coating station, it is at a temperature between 70°C and 150°C,

- preferably between 100°C and 130°C;
- extrusion, in the first coating station, of a molten sheet of polyester composed of one or more layers of polyester;
 - 5 - coating of the substrate by pressing the molten sheet against a surface of the substrate;
 - transportation of the strip coated on one side with polyester to a second coating station and heating the strip so that, before coating, it is
 - 10 at a temperature of between 70°C and 130°C, preferably between 90°C and 120°C;
 - coextrusion, in a second coating station, of a sheet comprising a polyolefin top layer and a modified polyolefin adhesion layer;
 - 15 - coating of the substrate with the molten sheet in the presence of ozone by pressing it with the adhesion layer against the surface of the substrate;
 - heating the coated substrate so that it assumes
 - 20 a temperature which is above the melting point of the polyolefin applied;
 - cooling of the coated substrate.




Fig.1

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/03001

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B32B31/30 B32B15/08 B29C47/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 96 32202 A (ALUMINUM CO OF AMERICA ; LEVENDUSKY THOMAS L (US); LARSEN ROBERT B) 17 October 1996 see page 1, paragraph 1 see page 8, last paragraph - page 9, paragraph 1 see page 32, paragraph 1 - page 33, paragraph 1 see figures ---	1,2
A	PATENT ABSTRACTS OF JAPAN vol. 017, no. 336 (M-1435), 25 June 1993 & JP 05 042650 A (NIPPON STEEL CORP), 23 February 1993 see abstract --- -/--	1,2



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

14 September 1998

Date of mailing of the international search report

25/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Lanaspeze, J

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/03001

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 312 308 A (MB GROUP PLC) 19 April 1989 see page 4, line 12 - line 33 ---	1,2
A	EP 0 067 060 A (TAIYO STEEL) 15 December 1982 see page 3, line 5 - line 16 see page 5, line 27 - page 6, line 10; figures ---	1,2
A	DE 195 29 583 A (BASF LACKE & FARBEN) 13 February 1997 see column 1, line 43 - line 53 see column 3, line 28 - line 35 see column 3, line 56 - column 4, line 31 see figure ---	1,2
A	US 4 519 863 A (LANDGRAF HELMUT ET AL) 28 May 1985 see abstract see column 1, line 35 - column 2, line 65 ---	1
A	PATENT ABSTRACTS OF JAPAN vol. 095, no. 011, 26 December 1995 & JP 07 227932 A (TOPPAN PRINTING CO LTD), 29 August 1995 see abstract ---	1,2
A	PATENT ABSTRACTS OF JAPAN vol. 007, no. 024 (M-189), 29 January 1983 & JP 57 178832 A (DAINIPPON INSATSU KK), 4 November 1982 see abstract ---	1,2
A	PATENT ABSTRACTS OF JAPAN vol. 017, no. 248 (M-1411), 18 May 1993 & JP 04 368845 A (MITSUBISHI PETROCHEM CO LTD), 21 December 1992 see abstract -----	1,2

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/03001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9632202 A	17-10-1996	EP 0820353 A	28-01-1998
EP 0312308 A	19-04-1989	AU 606768 B	14-02-1991
		AU 2554888 A	02-05-1989
		BG 51347 A	15-04-1993
		CA 1286965 A	30-07-1991
		CN 1032764 A,B	10-05-1989
		DE 3875053 A	05-11-1992
		DK 292389 A,B,	07-08-1989
		ES 2052739 T	16-07-1994
		FI 892907 A,B,	14-06-1989
		WO 8903308 A	20-04-1989
		GB 2211139 A,B	28-06-1989
		GR 3005914 T	07-06-1993
		HK 70195 A	19-05-1995
		JP 8022581 B	06-03-1996
		JP 2501641 T	07-06-1990
		KR 9510577 B	20-09-1995
		PL 163975 B	30-06-1994
		PL 161515 B	30-07-1993
		PT 88739 A,B	31-07-1989
		SG 9590732 A	01-09-1995
		RU 2060163 C	20-05-1996
		TR 25919 A	01-11-1993
		US 4980210 A	25-12-1990
EP 0067060 A	15-12-1982	JP 1680842 C	13-07-1992
		JP 3041342 B	21-06-1991
		JP 57203545 A	13-12-1982
DE 19529583 A	13-02-1997	WO 9706955 A	27-02-1997
US 4519863 A	28-05-1985	DE 3121773 A	16-12-1982
		AT 384579 B	10-12-1987
		BE 893264 A	16-09-1982
		CA 1183668 A	12-03-1985
		CH 656345 A	30-06-1986
		CS 8203840 A	13-02-1984
		FR 2506663 A	03-12-1982
		GB 2102328 A,B	02-02-1983

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/03001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4519863 A		JP 57195635 A	01-12-1982
		NL 8200751 A	16-12-1982
